



# Conplast WP100

## Concrete integral waterproofing admixture

### Uses

As an integral waterproofer for:

- Structural and precast concrete
- Sand : Cement renders
- Floor screeds
- Mortars and Plasters

### Advantages

- Allows a reduction in mix water content to be made without affecting workability, so reducing permeability.
- Provides integral protection, ensuring reduced permeability throughout the concrete and mortars.
- Integral protection is maintained even if surface damage occurs, unlike applied surface films or coatings.
- Lower water:cement ratio improves compressive strength at the same workability.
- Formulated for use in the Middle East.

### Description

Conplast WP100 is a chloride free integral waterproofing admixture and is supplied as a white powder. It is formulated from a blend of hydrophobic materials; which together form a matrix of insoluble, water resistant material within the cement paste.

The plasticisers in Conplast WP100 also improve the effectiveness of water in the concrete and sand:cement mix, enabling desired levels of workability to be obtained with lower water contents. This produces a mix with a reduced water:cement ratio and therefore reduced permeability.

### Properties

<b>Form</b>	: White powder
<b>Chloride Content</b>	: Nil to BS5075

### Typical dosage

The optimum dosage of Conplast WP100 to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use.

This allows the optimisation of admixture dosage and mix design and provides a complete assessment of the mix. As a guide, an addition rate of 1.3% - 2% by weight of cement.

### Use at other dosages

Dosages other than those given on this sheet may be used to meet particular mix requirements provided that adequate supervision is available. Compliance with requirements must be assessed through trial mixes. Contact the local Fosroc representative for any further advice.

### Instructions for use

### Compatibility

Conplast WP100 is compatible with other Fosroc admixtures used in the same concrete mix. All admixtures should be added to the mix separately and must not be mixed together prior to addition. The resultant properties of mixes containing more than one admixture should be assessed by the trial mix procedure recommended on this data sheet. Conplast WP100 is suitable for use with all types of Portland cements and cement replacement materials such as PFA, GGBFS and microsilica.

### Dispensing

The correct quantity of Conplast WP100 should be measured by means of a suitably accurate device; and then added to the concrete during the mixing process either by hand, or mechanically. Contact the Fosroc Technical Service Department for advice regarding suitable equipment and its installation.

### Effects of overdosing

An overdose of double the intended dose of Conplast WP100 may result in increased retardation and workability.

### Curing

As with all structural concrete and sand:cement mixes, good curing practice should be maintained, particularly in situations where an overdose has occurred. Water spray, wet Hessian or a Concure spray applied curing membrane should be used.

### Limitations

The use of Conplast WP100 will not make poor quality concrete waterproof. Good concrete practice must be followed at all times. Well graded aggregates must be used and a minimum cement content of 300kg/m<sup>3</sup> is usually recommended. Adequate waterstops must be provided between lifts of concrete and floor bays.

# Conplast WP100

---

## Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

## Estimating

### Supply

<b>Conplast WP100</b>	:	1kg pack
-----------------------	---	----------

## Storage

When stored in warehouse conditions below 35°C, Conplast WP100 will have a shelf life of 12 months.

## Precautions

### Health and safety

Conplast WP100 is mildly alkaline and should not be swallowed or allowed to come into contact with skin and eyes.

Wear suitable protective gloves and goggles. In case of contact with the skin, wash immediately with soap and water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

For further information consult the Safety Data Sheet available for this product.

### Fire

Conplast WP100 is an inert, non-flammable material.

### Cleaning and disposal

Spillages of Conplast WP100 should be removed by water. The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.



Fosroc Jordan

P.O.Box 253,  
King Abdullah II Industrial State  
Sahab 11512, Jordan  
[www.fosroc.com](http://www.fosroc.com)

### Important note:

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

---

**telephone:**  
+962 (6) 5359562

**fax:**  
+962 (6) 5359563

**email:**  
infojordan@fosroc.com

Registered Office: P.O.Box 253, King Abdullah II Industrial State, Sahab 115512, Jordan

